

Technical Data Sheet

Polybutadiene Rubber (WCMBR)

CHEMICAL DESCRIPTION:	Polybutadiene Rubber
PROPERTIES	
ASTM classification:	BR
Typical applications:	Winter tyres
Advantages :	Good tensile strength Good low temperature performance
Disadvantages:	Poor resistance to oils and non-polar solvents Poor steam resistance Poor ozone and weathering resistance Reduced resilience and abrasion resistance cf. NR and SBR
Available hardness range (Sh. A):	40 - 90
Upper continuous service temp.(°C):	100
Min. temp. for sealing applications(°C):	-60
Minimum non-brittle temp.(°C):	-90
Tensile strength (up to):	20 MPa
Elongation at break (up to):	550%

N.B. With all compounds, differing hardness's can affect final properties of the mix.

COMPOUND



Certificate Number: 14352
ISO 9001



Care should be taken in selecting the most suitable quality for each application. Advice is available, but final responsibility remains with the customer.

www.epdm.co.uk

E-Mail: Sales@epdm.co.uk

Contact

Telephone: +44 (0)1625 573971
FAX: +44 (0)1625 573250
Munsch & Co/PTM Ltd
Units AG2/3 Clarence Mill
Clarence Road, Bollington
Macclesfield, Cheshire
SK10 5JZ
United Kingdom