

# Technical Data Sheet


## White Food Quality Natural Rubber WCMN03

**ELASTOMERS**

**CHEMICAL DESCRIPTION:** Polyisoprene

**PHYSICAL PROPERTIES**

TENSILE STRENGTH: 3.5 MPa  
 COMPRESSION SET: 35%  
 22 Hours @ 70°C  
 ELONGATION AT BREAK: 300% Min.  
 ABRASION RESISTANCE: 250mm<sup>3</sup>  
 HARDNESS RANGE: 50° Sh. A +/- 5°  
 HEAT RESISTANCE: -40° - +90°C  
 OZONE RESISTANCE: Poor



**CHEMICAL RESISTANCE**

WATER: Good to Excellent  
 DILUTE ACIDS & BASES: Good  
 ALKALIS: Good  
 OILS: Poor  
 KETONES: Fair  
 FUELS & PETROLEUM SOLVENTS: Poor

Recommended for low to medium cost products where good resilience and toughness are prime considerations. Not recommended where resistance to heat or oils is required.

No rubber compound has formal FDA approval as only raw materials which are used to make a compound are given approval by the FDA. All the ingredients in this formulation have been checked against the latest update of the CFR21 FDA 177-2600 ingredient listings and are present at the level permitted.

This grade also complies with EC1935/2004.



EC1935:2004



Complies with FDA Food Contact Regulation 21 CFR177-2600



Certificate Number: 14352  
 ISO 9001



Care should be taken in selecting the most suitable quality for each application. Advice is available, but final responsibility remains with the customer.

[www.epdm.co.uk](http://www.epdm.co.uk)

E-Mail: [Sales@epdm.co.uk](mailto:Sales@epdm.co.uk)

**Contact**

Telephone: +44 (0)1625 573971  
 FAX: +44 (0)1625 573250  
 Munsch & Co/PTM Ltd  
 Units AG2/3 Clarence Mill  
 Clarence Road, Bollington  
 Macclesfield, Cheshire  
 SK10 5JZ  
 United Kingdom